



Technical Data

Product: Polypro® SRP40

Description: Low Density Semi-rigid Packaging Foam System

Product Type: Water Blown Pour Foam

Uses: Foam-in-Place and Molding applications

Shipping Containers: Returnable or refillable pressure cylinders
Disposable 55 gallon drums
Disposable 275 gallon tote tanks

Recommended Dispensing Equipment: Foampro® P3000

Processing Conditions

Ratio A:B (by weight): 110:100 to 140:100
Chemical Temperature: 125 to 135° F
Cream Time: Immediate
Rise Time: 20-25 seconds
Tack Free Time: 25-25 seconds
Free Rise Density: 0.38-0.42 pounds/cubic foot

Chemical Properties

| | “A” Component | “B” Component |
|---------------------------------|----------------------|----------------------|
| Specific Gravity @ 75° F | 1.23 | 1.03 |
| Viscosity, cps @ 75° F | 150-200 | 500-700 |

SAFETY WARNING: Polyurethane foam is combustible and may constitute a fire hazard if improperly used or stored. Read the Material Safety Data Sheet for further safety precautions.

DISCLAIMER: This information is believed to be true and accurate, but all recommendations are made without warranty, since the conditions of use are beyond the control of Polyfoam Products, Inc. (PPI). PPI requests that customers inspect and test our product before use, and satisfy themselves as to contents and suitability. PPI assumes no responsibility for the product relative to its performance or injury resulting from its use. Liability, if any, is limited to replacement of materials.